

The Role of Bronsted Acid Sites in Cleavage of 1-Octadecene Compounds (Long Carbon Chain) Being a Compound with Short Carbon Chain Bonds

Donatus Setyawan Purwo Handoko^{1*}, Triyono²

¹University of Jember

²Gadjah Mada University

Corresponding Author: Donatus Setyawan Purwo Handoko

kreka_zeolit@yahoo.com

ARTICLE INFO

Keywords: Impregnation, Zeolite, Fluid Bed, Cracking

Received : 2 July

Revised : 18 August

Accepted: 21 September

©2024 Handoko, Triyono: This is an open-access article distributed under the terms of the [Creative Commons Attribution 4.0 International](https://creativecommons.org/licenses/by/4.0/).



ABSTRACT

Research has been carried out on acid zeolite to break long carbon chain bonds into shorter ones using acid zeolite. The catalyst used is made from zeolite which is treated with calcination with nitrogen at a temperature of 400 oC for 2 hours then followed by hydrothermal treatment at a temperature of 500 oC for 2 hours and then impregnation with Ni metal, then oxidation with oxygen for 3 hours. at a temperature of 500 oC. Then the cracking process was carried out on the methyl oleate compound with a zeolite catalyst impregnated with Ni metal using a Fluid Bed reactor operated at a temperature of 500 oC for 30 minutes while hydrogen gas was flowing at a speed of 10 mL/minute. The results obtained are that based on analysis using GCMS are as follows: the process of breaking down alkane compounds obtained from the interaction between the catalyst surface in the upper layer can interact again with the catalyst surface in the lower layer, in line with the feed flow. This interaction may result in shorter alkane compounds and other forms of compounds such as cyclic, aromatic or isomeric forms

INTRODUCTION

The use of zeolite as an active metal carrier in the manufacture of metal/carrier system catalysts requires paying attention to the properties of the natural zeolite itself such as: zeolite acidity, high surface area, porous structure. These properties are very important in the use of natural zeolites as active metal carriers in catalyst preparation.

Catalyst material with a crystal structure of MCM-41 with a mesoporous pore size with a surface area of between 550 to 1200 m²/g and has an average pore size of 1.8 to 2.8 nm. MCM-41 catalyst shows high activity for palm oil cracking. The MCM-41 material is selective for the formation of linear hydrocarbons, especially C₁₃. The liquid product yield decreases with increasing catalyst surface area. Selectivity for gasoline increases while diesel selectivity decreases with conversion from palm oil.

LITERATURE REVIEW

According to Twaiq (2003), catalytic cracking of palm oil to produce liquid hydrocarbon fuel has been studied in a fixed bed microreactor operated at atmospheric pressure, temperature 723 K and WHSV 2.5 h⁻¹ using mesoporous molecular sieve MCM-41. Mesoporous aluminosilicate with an S/Al ratio of up to 50 was synthesized using the hydrothermal method.

METHODOLOGY

1. Research Materials and Tools

The research materials used were: Wonosari natural zeolite from PT Prima Zeolita, materials from E.Merck and quality p.a. consisting of: oleic acid (91.59 %), 1-octadecanol 95 %, 1-octadecene 90 %, HCl 37 % (v/v), HF 40 % (v/v), NH₄Cl, Na₂SiO₃, Ni(NO₃)₂·6H₂O 97 %. Other materials such as: oxygen, nitrogen and hydrogen gas (P.T. Samator Gas), pH paper.

The equipment required for the research is: a set of fixed bed reactors, thermocouples, thermometers, ovens, hot-plates, laboratory glassware, analytical balance (Mettler RE 200), atomic absorption spectroscopy (AAS, Varian FS 220), GC-MS (Shimadzu QP-2010S), surface area analyzer NOVA 1000 (Quantachrome Nova Win2 version 2.2), X-ray diffractometer (XRD, Shimadzu-6000).

2. Research Procedures

This research procedure is divided into several stages such as catalyst preparation, making methyl 9-octadecenoate, hydrogenation of methyl 9-octadecenoate with a ZSiA catalyst, catalytic hydrogenation of 1-octadecanol with a ZSiA catalyst, hydrocracking of 1-octadecene with a Ni/ZsiA catalyst.

2.1. Ni/ZSiA Catalyst Preparation

Zeolite with a passing size of 100 mesh is soaked in distilled water and washed while stirring. Then soaked in 2% HF for 30 minutes, then washed with distilled water, repeated 3 times, then dried in the oven at a temperature of 120 oC for 3 hours. Next, it was oxidized with oxygen at a temperature of 500 oC for 2 hours and calcined with nitrogen at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute to obtain a Z catalyst (Handoko, 2001).

Next, the Z catalyst was washed using a 2 M HCl solution with a ratio of zeolite: HCl solution = 1: 2 (v/v) while stirring for 20 to 30 minutes (Zhang, 1999). Next, the zeolite samples were washed using distilled water until pH = 6 and dried in an oven at a temperature of 120 oC for 3 hours and continued with oxidation using oxygen gas at a flow rate of 20 mL/minute at a temperature of 500 oC for 2 hours and calcination with nitrogen gas at a rate of flow 20 mL/minute at a temperature of 500 oC for 2 hours. Then to the Z catalyst in a beaker, 5% (w/w) of Na-Silicate (Na_2SiO_3) was added which was dissolved in distilled water and then heated at a temperature between 80 oC to 90 oC for 24 hours while stirring using a magnetic stirrer. Then the sample was cooled and continued with oxidation with oxygen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute and continued with calcination with nitrogen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute to obtain a ZSi catalyst.

The ZSi catalyst was cooled and a 2 M NH_4Cl solution was added to the beaker with a ratio of 1: 2 (v/v) and the mixture was heated again at a temperature of 90 oC for 4 hours with a magnetic stirrer (Zhang, 1999). Then cooled and continued with the oxidation process using oxygen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute and continued with calcination with nitrogen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute to obtain the ZSiA catalyst. .

Impregnation of Ni metal (Ni 2% (w/w)) on the surface of the ZSiA catalyst was carried out using the wet impregnation method. 9.91 g of $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ salt was dissolved in 100 mL of distilled water while stirring until homogeneous, then 100 g of sample (ZSiA catalyst) was added. Then it is heated and evaporated at a temperature of 80 oC to 90 oC (at 1 atm) while stirring so that the water component will slowly evaporate. After the water component has evaporated, the sample is placed in an oven at a temperature of 120oC for 2 hours and continued with the oxidation process with oxygen gas at a temperature of 500oC for 2 hours with a gas flow rate of 20 mL/minute and reduction at a temperature of 500oC with hydrogen gas flowing at 20 mL/minute to obtain a Ni/ZSiA catalyst (Handoko, 2001).

Each stage of treatment is analyzed for metal content using AAS, acidity using the gravimetric method, crystallinity using XRD and surface area using the BET method.

The ZSi catalyst was cooled and a 2 M NH_4Cl solution was added to the beaker with a ratio of 1: 2 (v/v) and the mixture was heated again at a temperature of 90 oC for 4 hours with a magnetic stirrer (Zhang, 1999). Then cooled and continued with the oxidation process using oxygen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute and continued with calcination with nitrogen gas at a temperature of 500 oC for 2 hours with a gas flow rate of 20 mL/minute to obtain the ZSiA catalyst. .

Impregnation of Ni metal (Ni 2% (w/w)) on the surface of the ZSiA catalyst was carried out using the wet impregnation method. 9.91 g of $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ salt was dissolved in 100 mL of distilled water while stirring until homogeneous, then 100 g of sample (ZSiA catalyst) was added. Then it is

heated and evaporated at a temperature of 80 oC to 90 oC (at 1 atm) while stirring so that the water component will slowly evaporate. After the water component has evaporated, the sample is placed in an oven at a temperature of 120oC for 2 hours and continued with the oxidation process with oxygen gas at a temperature of 500oC for 2 hours with a gas flow rate of 20 mL/minute and reduction at a temperature of 500oC with hydrogen gas flowing at 20 mL/minute to obtain a Ni/ZSiA catalyst (Handoko, 2001).

Each stage of treatment is analyzed for metal content using AAS, acidity using the gravimetric method, crystallinity using XRD and surface area using the BET method.

RESULTS AND DISCUSSION

Catalytic hydrogenation of 1-octadecanol with a ZSiA catalyst in a fixed bed reactor at a temperature of 400 oC produced 49.60% alkane and alkene products with a chain length < C18. The catalytic hydrogenation mechanism of 1-octadecanol is thought to follow two main stages, namely reduction of the alcohol group to alkene and breaking of the alkene bond to form shorter chain alkanes and alkenes. The mechanism is as follows,




Figure 1. Conversion of 1-Octadecanol to 1-Octadecene

According to Campbell (1988), the 1-octadecene compound then forms its isomers, namely 5-octadecene and 9-octadecene with relative concentrations of 14.37 and 10.40%. The conversion mechanism of 1-Octadecene is as follows,




Figure 2. Isomerization of 1-Octadecene

Furthermore, the compounds 1-octadecene, 5-octadecene and 9-octadecene undergo further cracking to form shorter alkane and alkene compounds.




Figure 3. Conversion of 1-Octadecene to Heptadecane and Methane

Reactants that have been adsorbed on the surface of a solid can experience a "migration" event, namely the movement of molecules in one dimensional plane. Molecules that migrate (in a fixed adsorbed position) are very likely to collide with other molecules.




Figure 4. Illustration of Ethane Adsorbed on the Catalyst Surface

Thus, the more reactant molecules are adsorbed on the surface of the catalyst solid, the greater the probability of collisions occurring and producing reaction products. Collisions (encounters) between reactant molecules have less energy but occur between active reactant molecules so a lower activation energy is required.

According to Campbell (1988), the long chain bond breaking products can be alkanes or short chain alkenes as shown in the mechanism in the picture below. In the hydrogenation process on the catalyst surface, at a hydrogen flow rate of 10 mL/minute, both conditions show maximum results. At a hydrogen flow rate of 10 mL/minute, hydrogen adsorption onto the catalyst surface was very good. At a hydrogen flow rate of 10 mL/minute, relatively more hydrogen is adsorbed on the catalyst surface quantitatively compared to a faster hydrogen flow rate, so it is possible for the hydrogen to be in a condensed state and undergo dissociation and migration. The relatively fast migration of hydrogen allows the possibility of collisions with 1-octadecene molecules and the production of reaction products <C12 which is greater.




Figure 4. A Beta Shift Occurs and a Short Compound is Formed

The process of breaking down alkane compounds obtained from the interaction between the catalyst surface in the upper layer can interact again with the catalyst surface in the layer below. In line with the feed flow. This interaction may result in shorter alkane compounds and other forms of compounds such as cyclic, aromatic or isomeric forms. The following is an illustration of breaking a long chain into a short chain.




Figure 5. Event of Breaking a Long Chain into a Short Chain

CONCLUSIONS AND RECOMMENDATIONS

In breaking long chain bonds into short chains, it will be easier to interact with the presence of Bronsted acid sites to form short chain bonds. The acidity and strength of acid of a catalyst have different meanings. According to Satterfield (1982), the acidity of a catalyst is defined as the ability of the catalyst to adsorb ammonia base due to the presence of Bronsted acid sites and Lewis acid sites on the catalyst surface. Acid strength is defined as the ability of the catalyst surface containing Bronsted acid sites and Lewis acid sites to interact with reactants (organic compounds). The relationship between acidity and acid strength is inverse.

FURTHER STUDY

This research still has limitations so further research is needed related to the effect of capital and E-commerce on production and income of micro, small and medium furniture businesses in order to perfect this research and increase insight for readers.

REFERENCES

- Anderson, J.R. and Boudart, M., 1981, *Catalysis Science and Technology*, First Edition, Springer Verlag, Berlin.
- Augustine, R.L., 1996, *Heterogeneous Catalysis for Chemist*, Marcel Dekker Inc., New York.
- Bartholomew, C. H. and Farrauto, R.J., 2006, *Fundamentals of Industrial Catalytic Processes*, 2nd edition, John Wiley and Sons Inc., New Jersey.
- Belitz, H.D., and Grosch, W., 1999, *Food Chemistry*, 2nd edition, Springer-Verlag, Berlin.
- Bell, A.T., 1987, *Support and Metal Support Interaction in Catalyst Design*, John Wiley & Sons, New York.
- Boudart, M. and Bell A.T., 1987, *Catalyst Design*, 1st edition, A Wiley-Interscience Publication, New York.
- Brands, D.S., Poels, E.K., Dimian, A.C. and Bliet, A., 2002, *Solvent-Based Fatty Alcohol Synthesis Using Supercritical Butane : Flowsheet Analysis and Proses Design*, J. Am. Chem, Vol 79 (1).
- Campbell, I. M., 1988, *Catalysts at Surfaces*, Chapman and Hall Ltd., New York.

- Costas, S. T., 2000, Dealuminated H-Y Zeolite: Influence of The Degree and The Type of Dealumination Method on Structural and Acidic Characteristics of H-Y Zeolite, *Ind. Eng. Chem.*:39, 307-319.
- Demirbas, A. 2003. "Biodiesel fuels from vegetable oils via catalytic and non-catalytic supercritical alcohol transesterifications and other methods: a survey". *Energy Convers. Manage.*, 44, 2093-2109.
- Demirbas, A., 2003, Fuel Conversional Aspect of Palm Oil and Sunflower, *Energy Sources J.*, 5, 25, 154-167.
- Demirbas, A., 2006, Biodiesel Production Via Non Catalytic SCF Method and Biodiesel Fuel Characteristics, *Energy Convers. Manage.*, 47, 15-16, 2271 - 2282.
- Derouane, E.G., 1992, *Zeolite Microporous Solids: Synthesis, Structure, and Reactivity*, Kluwer Academic Publishers, London.
- Dyer, A., 1988, *An Introduction to Zeolite Molecular Sieves*, John Wiley and Sons Ltd., Chichester.
- Fessenden, R.J. and Fessenden, J.S., 1986, *Organic Chemistry*, 3rd edition, Wadsworth, California.
- Gasser, R.P.H., 1987, *An Introduction to Chemisorption and Catalysis by Metal*, Oxford Science Publication, Oxford.
- Groggins, P.H., 1952, *Unit Processes in Organic Synthesis*, Mc.Graw-Hill Book Company, Inc., New York.
- Guisnet, M., 2002, "Coke" Molecules Trapped in The Micropores of Zeolites as Active Species in Hydrocarbon Transformations, *J. Mol. Catal.*, 182-183, 367-382.
- Hamdan, H., 1992, *Introduction to Zeolites: Synthesis, Characterization, and Modification*, Universiti Teknologi Malaysia, Penang.
- Harber, J., 1991, *Manual on Catalyst Characterization*, *Pure and Appl. Chem.*, 63, 9, 1227-1246.
- Ketaren, 1986, *Pengantar Teknologi Minyak dan Lemak Pangan*, Universitas Indonesia Press, Jakarta.
- Kloprogge T.J., Doung Loc V., and Ray L. Frost, 2005, A Review of The Synthesis and Characterization of Pillared Clays and Related Porous Material for Cracking of Vegetable Oil to Produce Biofuel, *Env. Geo. J.*, 47, 7, 967-981.

- Knothe, G., 2000, Monitoring a Progressing Transesterification Reaction by Fiber-Optic Near Infrared Spectroscopy with Correlation to ¹H Nuclear Magnetic Resonance Spectroscopy, *J. Am. Oil Chem. Soc.*, 77, 94, 489-493.
- Knothe, G., Dunn, R. O., and Bagby, M. O., 1997, Biodiesel: The Use of Vegetable Oils and Their Derivatives as Alternative Diesel Fuels, *Fuels and Chemicals from Biomass, ACS Symposium Series, V*, 666.
- Kunkeler P.J., 1998, Zeolite Beta: The Relationship between Calcination Procedure, Aluminum Configuration, and Lewis Acidity, *J. Catal.* 180, 234.
- Laidler, K., J., 1950, *Chemical Kinetics*, 1st edition., McGraw-Hill Book Company, Inc., New York.
- Lowell, S. and. Shields, J.E, 1984, *Powder Surface Area and Porosity*, 2nd edition, Chapman and Hall, New York.
- Martinez, T.J., Diaz, C.M.J., Cambolor, M.A., Fornes, V., Maesen, T.L.M. and Corma, A., 1999, The Catalytic Performance of 14-Membered Ring Zeolites, *J. Catal.*, 182, 463-469.
- May, C. Y., 2004, Transesterification of Palm Oil: Effect of Reaction Parameters, *J. Oil Palm Res.*, 16, 2, 1-11.
- Page Le, J. F., Cosyns, J. and Courty, P., 1987, *Applied Heterogenous Catalyst*, edisi 1987, Imprimerie Nouvelle, Saint Jean de Braye, Paris.
- Perry, R.H. dan Green, D.W., 1997, *Perry's Chemical Engineer's Handbook*, Mc.Graw-Hill Companies. Inc., New York.
- Pioch, D. and Vaitilingom, G., 2005, Palm Oil and Derevatives: Fuels or Potensial Fuels?, *Corps Gras, Lipides*, 12, 2, 161-9.
- Rajeshwer, D., Sreenivasa Rao, G., Krishnamurthy, K., R., Padmavathi, G., Subrahmanyam, N. dan Jagdish, D. Rachh, 2006, Kinetics of Liquid - Phase Hydrogenation of Straight Chain C10 to C13 Di-Olefins Over Ni/Al₂O₃ Catalyst, *International Journal of Chaemical Reactor Engineering*, Vol. 4, Article A17
- Ramesh, B.D., 2000, Hydrogenation of 1-alkenes Catalysed by Anchored Montmorillonite Palladium (II) Complexes : a Kinetic Study, *Trans. Met. Chem*, 25, 6, 639-643.
- Sang, O.Y., 2003, Biofuel Production From Catalytic Cracking of Palm Oil, *Energy Sources J*, 9, 25.

- Santos, L.T., 2003, Nickel Activation for Hydrogenolysis Reaction on USY Zeolite, *Catal. Lett.* 92, 81.
- Satterfield, C.N., 1980, *Heterogeneous Catalysis in Practice*, McGraw-Hill Book Co., New York.
- Sibilia, J.P., 1996, *A Guide to Materials Characterization and Chemical Analysis*, 2nd Edition. VCH Publishers, Inc., New York.
- Smith, K., 1992, *Solid Support and Catalyst in Organic Synthesis*, Ellis Horwood PTR, Prentice Hall, London.
- Treacy, M.M.J., and Higgins, J.B., 2001, *Collection of Simulated XRD Powder Patterns for Zeolite*, Elsevier, Amsterdam.
- Twaiq F.A., Asmawati Noor M. Zabidi, Abdul Rahman Mohamed and Subhash Bhatia, 2003, Catalytic Conversion of Palm Oil Over Meso Porous Aluminosilicate MCM 41 for The Production of Liquid Hydrocarbon Fuel, *Fuel Process Technol*, 84, 1-3, 105 - 120.
- Van Santen, R.A. and Kramer, G.J., 1995, Reactivity Theory of Zeolitic Bronsted Acidic Sites, *J. Am. Chem. Soc : Chem. Rev*, 95, 637-669.
- Wu Jing, 2005, *Kinetics and Reactor Design*, Department of Chemical Engineering, Hong Kong.
- Yoon, C., 1997, Hydrogenation of 1,3-butadiene on Platinum Surfaces of Different Structures, *Catal. Lett*, 46, 37.
- Zhang, W. and Smirniotis, P.G., 1999, Effect of Zeolite Structure and Acidity on the Product Selectivity and Reaction Mechanism for n-Octane Hydroisomerization and Hydrocracking, *J. Catal.*, 182, 400-416.
- Zhilong Yao, 2008, *Research on Hydrogenation of FAME to Fatty Alcohol at Supercritical Conditions*, Beijing Institute of Petrochemical Technology, Beijing.